


IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): ~~Solid~~ A solid pigment preparations preparation
comprising ~~as essential constituents~~

(A) from 60% to 85% by weight of at least one organic pigment,

(B) from 0.1% to 15% by weight of at least one pigment derivative of the general
formula I



where

P is the residue of the core structure of an organic pigment selected from the group consisting of quinophthalone and phthalocyanine pigments;

T¹ and T² are independently a chemical bond, -CONR¹- or -SO₂NR¹-;

B¹ and B² are independently a chemical bond, C₁-C₈-alkylene or phenylene;

X and Y independently represent identical or different groups -SO₃⁻Ka⁺ or -COO⁻Ka⁺;

m and n are each a rational number from 0 to 3 subject to the proviso that
 $1 \leq m+n \leq 4$;

Ka⁺ is H⁺, Li⁺, Na⁺, K⁺, N⁺R²R³R⁴R⁵ or a mixture thereof;

R¹ is hydrogen; C₁-C₄-alkyl; unsubstituted or C₁-C₁₈-alkyl-substituted phenyl; or unsubstituted or C₁-C₁₈-alkyl-substituted naphthyl;

R², R³, R⁴ and R⁵ are independently hydrogen; C₁-C₃₀-alkyl; C₃-C₃₀-alkenyl; C₅-C₆-cycloalkyl, unsubstituted or C₁-C₂₄-alkyl-substituted; unsubstituted or C₁-C₂₄-alkyl- or C₂-C₂₄-alkenyl-substituted phenyl; unsubstituted or

C₁-C₂₄-alkyl- or C₂-C₂₄-alkenyl-substituted naphthyl; a radical of the formula -[CHR⁶-CHR⁷-O]_x-R⁸ where the repeat units -[CHR⁶-CHR⁷-O] can vary for x > 1;

R⁶, R⁷ and R⁸ are independently hydrogen or C₁-C₆-alkyl;

x is an integer ≥ 1,

and

(C) from 14.9% by weight to 39.9% by weight of at least one surface-active additive selected from the group consisting of the nonionic polyethers comprising no primary amino group, said polyethers' acidic phosphoric, phosphonic, sulfuric and/or sulfonic esters, the salts of these esters and the alkyl- and alkylarylsulfonic acids, their salts and their condensation products with formaldehyde.

Claim 2 (Currently Amended): ~~Pigment preparations~~ The solid pigment preparation as claimed in claim 1 in the form of granules having an average particle size from 50 to 5 000 µm and a BET surface area of ≤ 15 m²/g.

Claim 3 (Currently Amended): ~~Pigment preparations~~ The solid pigment preparation as claimed in claim 1 ~~or 2~~, wherein component (C) is at least one additive selected from the group consisting of the alkylene oxide copolymers, the reaction products of alkylene oxides with alcohols, amines, aliphatic carboxylic acids or carboxamides, the acidic phosphoric, phosphonic, sulfuric and sulfonic esters of these alkylene oxide compounds, the salts of these esters and the alkylphenyl- and alkyl-naphthalenesulfonic acids, their salts and their condensation products with formaldehyde.

Claim 4 (Currently Amended): A process for producing pigment preparations as claimed in ~~any of claims 1 to 3, which comprises~~ claim 1, comprising wet-comminuting the pigment (A) in aqueous suspension which comprises some or all of additive (C) and, if ~~desired~~ optionally, some or all of pigment derivative (B) and also, if ~~desired~~ optionally, prior or subsequent neutralization of the suspension with a base and then drying the suspension, if necessary after the rest of pigment derivative (B) and additive (C) has been added.

Claim 5 (Currently Amended): A process for coloration of macromolecular organic and inorganic materials, ~~which comprises~~ comprising incorporating pigment preparations as claimed in ~~any of claims 1 to 3~~ claim 1 in these materials by stirring or shaking.

Claim 6 (Currently Amended): ~~[[A]]~~ The process as claimed in claim 5 for coloration of coatings, paints, inks, including printing inks, and finish systems where the liquid phase comprises water, organic solvents or mixtures of water and organic solvents.

Claim 7 (Currently Amended): A process for coloration of macromolecular organic and inorganic materials ~~using~~ with color-mixing systems, ~~which comprises using~~ comprising utilizing pigment preparations as claimed in ~~any of claims 1 to 3~~ claim 1 as mixing components.

Claim 8 (Currently Amended): A process for coloration of plastics, ~~which comprises~~ comprising incorporating pigment preparations as claimed in ~~any of claims 1 to 3~~ claim 1 in the plastics by extruding, rolling, kneading or milling. ~~Solid pigment preparations including pigment derivatives and surface active additives~~